

Electrolock-XP® (RoHS Compliant)

Property	Value	ASTM Test Method
Color	Granite Gray	
ESD	$10^8 - 10^{11}$ ohm/square	D4496
Machinability	Excellent	
Chemical Resistance	Excellent	
Heat Deflection Temperature	> 375°F	D648
Operating Temperature	> 500°F	none
Water Absorption	.20 max	D570
Specific Gravity	1.72	D792
Flexural Strength, PSI	55,000	D790
Warp	+/- .015"	TIR over entire sheet
Thickness Tolerance	+/- .005"	Over entire sheet
Thickness, mm	5, 6, 8, 10, 12	
Sheet Size	25" x 25" x various thicknesses	



17930 Great Lakes Parkway • Hiram, OH 44234 U.S.A.
t: 440.834.7500 • f: 440.834.7525 • www.electrolock.com
Contact Rich Reed for more info: rich@electrolock.com